

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): A heat conductive composite sheet comprising:

(a) a heat softening, heat conductive layer ~~containing~~ comprising a silicone resin and a heat conductive filler, and

(b) a heat conductive silicone rubber layer ~~containing~~ comprising a heat conductive filler.

Claim 2 (Original): The heat conductive composite sheet according to claim 1, wherein said silicone resin of said layer (a) is a polymer comprising at least one unit selected from the group consisting of  $\text{RSiO}_{3/2}$  units wherein R represents an unsubstituted or substituted hydrocarbon group of 1 to 10 carbon atoms, and  $\text{SiO}_2$  units.

Claim 3 (Currently Amended): The heat conductive composite sheet according to claim 1, wherein said silicone resin of said layer (a) ~~is comprised of~~ comprises a polymer comprising at least one unit selected from the group consisting of  $\text{RSiO}_{3/2}$  units, and  $\text{SiO}_2$  units, and an polydiorganopolysiloxane comprised of  $\text{R}_2\text{SiO}$  units and terminal  $\text{R}_3\text{SiO}$  units wherein in the formulas R each represent an unsubstituted or substituted hydrocarbon group of 1 to 10 carbon atoms.

Claim 4 (Currently Amended): The heat conductive composite sheet according to claim 1, wherein said heat conductive silicone rubber of said layer (b) ~~is comprised of~~ comprises a cured product of an addition reaction curable silicone rubber composition ~~containing~~ comprising a heat conductive filler.

Claim 5 (Currently Amended): The heat conductive composite sheet according to claim 1, wherein said heat conductive silicone rubber of said layer (b) ~~is comprised of~~ comprises a cured product of a condensation curable silicone rubber composition ~~containing~~ comprising a heat conductive filler.

Claim 6 (Currently Amended): The heat conductive composite sheet according to claim 1, wherein said heat conductive silicone rubber of said layer (b) is a cured product of a radical reaction curable silicone rubber composition ~~containing~~ comprising a heat conductive filler.

Claim 7 (Currently Amended): A process for producing a heat conductive composite sheet comprising:

(a) a heat softening, heat conductive layer formed of a composition comprising a silicone resin and a heat conductive filler, and

(b) a heat conductive silicone rubber layer ~~containing~~ comprising a heat conductive filler, said process comprising:

providing said heat conductive silicone rubber layer of (b),

optionally forming at least one intermediate layer on top of said heat conductive silicone rubber layer of (b), and

forming a layer of said composition on top of said heat conductive silicone rubber layer of (b) or, if said intermediate layer is present, on top of the intermediate layer.

Claim 8 (Currently Amended): A process for producing a heat conductive composite sheet comprising:

(a) a heat softening, heat conductive layer ~~containing~~ comprising a silicone resin and a heat conductive filler, and

(b) a heat conductive silicone rubber layer ~~containing~~ comprising a heat conductive filler, said process comprising:

providing said heat softening, heat conductive layer ~~containing~~ comprising a silicone resin and a heat conductive filler of (a),

forming a layer of a liquid, curable silicone rubber composition comprising a heat conductive filler on top of said heat softening, heat conductive layer of (a), and

curing said composition to form said heat conductive silicone rubber layer of (b).

Claim 9 (Original): The process according to claim 8, wherein said liquid, curable silicone rubber composition is an addition reaction curable silicone rubber composition.

Claim 10 (Original): The process according to claim 8, wherein said liquid, curable silicone rubber composition is a condensation curable silicone rubber composition.

Claim 11 (Currently Amended): A process for producing a heat conductive composite sheet comprising:

(a) a heat softening, heat conductive layer ~~containing~~ comprising a silicone resin and a heat conductive filler, and

(b) a heat conductive silicone rubber layer ~~containing~~ comprising a heat conductive filler, said process comprising:

subjecting a heat softening, heat conductive sheet ~~containing~~ comprising a silicone resin and a heat conductive filler, and a heat conductive silicone rubber sheet ~~containing~~ comprising a heat conductive filler to thermocompression bonding together.

Claim 12 (New): The heat conductive composite sheet according to claim 1, wherein at least the surface of the heat softening, heat conductive layer is capable of softening or melting at a temperature that ranges from 40°C to 100°C.

Claim 13 (New): The heat conductive composite sheet according to claim 1, wherein at least the surface of the heat softening, heat conductive layer is capable of softening or melting at a temperature that ranges from 40°C to 90°C.